



Ref. No : TBF / KA.26.B.014 / 00
Yayın Tarihi : 20 / 04 / 2007
Sayfa : 01 / 01

TEKNİK BİLGİ FORMU

KA-26-B-014

Ürün Tanımı

Renk

Uygulama Tavsiyeleri

Uygulama metodu

Uygulama viskozitesi, 20°C

Karışım oranı

Kuruma koşulları, %65 RH

Uygulama sıcaklığı

Uygulama kalınlığı

Yüzey hazırlığı

Yaş Boya Özellikleri

Ambalaj viskozitesi, 20°C

Amb. visk. de yoğunluk, 20°C

Amb. visk. de katı madde

Teorik kaplama alanı

Pratik kaplama alanı

Depolama ve Güvenlik Bilgileri

Depolama Süresi

Uyarılar

RAPİD ASTAR

Modifiye alkid reçineleri içeren, dolgu gücü yüksek hava kurumalı boyadır. Metal sanayinin hızlı kurumalı, saca iyi yapışan astar ihtiyacını karşılamak üzere geliştirilmiştir.

Fildişi (RAL 1014)

Sprey

20 ± 2 sn. / DIN CUP 4

Ağırlıkça %16±3 kadar TK0001 ile inceltir.

Toz kuruma : 3 - 6 dak. / 20°C

Dokunma kuruma : 6 - 10 dak. / 20°C

Tam kuruma : 6 - 7 gün / 20°C

5°C - 45°C

35 ± 5 mikron kuru film.

Boyanacak yüzey her türlü yağ, kir, toz ve nemden arındırılmış olmalıdır.

95 ± 5 sn. / DIN CUP 4

1.38 ± 0.04 gr/ml

%65 ± 2 (Ağ.)

1 kg boya ile 35 mikron kuru film bırakacak şekilde tatbik edildiğinde yaklaşık 9 m² alan kaplanabilir.

Yüzey pürüzlülüğü ve sıçrıntı kayıpları nedeniyle kesin bir değer verilemez. Aşağıdakiler yaklaşık değerler olarak alınabilir:

Büyük parçalar için : % 70 x Teorik kaplama alanı

Küçük parçalar için : % 50 x Teorik kaplama alanı

Orijinal ambalajının açılmaması durumunda 5°C - 40°C sıcaklıklar arasında, normal stoklama koşullarında en az 12 ay süreyle depolanabilir.

Yanıcıdır.

Etiket üzerindeki uyarılara bakınız. Taşınması, depolanması ve atıklarının yok edilmesi sırasında, ilgili yasa ve tüzüklere uyulmalıdır. Detaylı bilgi için Güvenlik Bilgi Formu' na başvurunuz.



Ref. No : TIS / KA.26.B.014 / 00
Issue Date : 20 / 04 / 2007
Page : 01 / 01

TECHNICAL INFORMATION SHEET

KA-26-B-014

Description

Color

Application Recommendations

Application method

Application viscosity, 20°C

Mixing ratio

Drying conditions, 65% RH

Application temperature

Film thickness

Surface preparation

Wet Paint Properties

Delivery viscosity, 20°C

Density on delivery visc., 20°C

Solid content on delivery visc.

Theoretical coverage

Practical coverage

Storage and Safety Information

Storage time

Warnings

RAPID PRIMER

Air-drying primer based on modified alkyd resins with high filling ability. It was developed for quick drying and good adhesion property demands of metal industry.

Ivory (RAL 1014)

Spray

20 ± 2 sec. / DIN CUP 4

Dilute with TK0001 thinner: 16±3 % by weight.

Dust Dry : 3 - 6 min. / 20°C

Touch Dry : 6 - 10 min. / 20°C

True Dry : 6 - 7 days / 20°C

5°C - 45°C

35 ± 5 microns dry film.

All surfaces to be coated should be clean, dry and free from contaminations.

95 ± 5 sec. / DIN CUP 4

1.38 ± 0.04 gr/ml

65 ± 2 % (by wt.)

Approximately 9 m² / 1 kg paint for 35 microns dry film thickness.

The practical coverage depends on the factors, such as shape of the construction, roughness of the substrate, method and conditions of application. A guideline for spraying is:

Large areas : Approx. 70% of the theoretical coverage.

Small areas : Approx. 50% of the theoretical coverage.

Minimum 12 months in unbroken original package at 5°C - 40°C.

Flammable.

See label for precautions. The user of this product is required to comply with the national statutory regulations for health, safety during transportation and at work and waste disposal. See the MSDS for detailed information.